

DIRECT

			% O.W.F.	C.INDEX	LIGHT FASTNESS	WASHING FASTNESS	RUBBING DRY	RUBBING WET
	2021675	Yellow PG	1.0	Y-142	4 - 5	3	4	4
	2021732	Yellow RL 165%	1.0	Y-86	5	3 - 4	4 - 5	3
	2021853	Yellow EFC LF Conc	1.0	Y-106	6	4	5	4
	202793	Orange TGL	1.0	O-34	5 - 6	3	3 - 4	3
	2021600	Orange GGL	1.0	O-39	5	4	5	3
	202714	Scarlet FG	1.0	R-224	3 - 4	4 - 5	3 - 4	3
	202203	Scarlet 4BS Conc	1.0	R-23	3 - 4	3	3	2
	202465	Red F3B	1.0	R-80	5	3	3	3
	2021717	Supra Red BWS-T	1.0	R-243	3	3	4 - 5	3
	202212	Nippon Pink B 200%	1.0	R-227	3	4-5	4	3
	2021190	Rubine BL-T	1.0	R-83:1	6	3	4 - 5	3
	202185	Turquoise FBL 400%	1.0	B-199	5-6	2-3	4	4
	2021841	Supra Blue FRRL-T	1.0	B-108	6 - 7	4	4 - 5	4 - 5
	2021920	Blue BRR 180%	1.0	B-71	6	4	5	3
	202886	Blue 4BL 220%	1.0	B-200	6	4	4-5	3
	2021724	Blue L4G	1.0	B-78	5	3 - 4	5	2 - 3
	2021828	Brown AGL 110%	1.0	Br-115	4 - 5	3 - 4	3 - 4	3
	2021958	Brown RL 130%	1.0	Br-116	4 - 5	4 - 5	3 - 4	3
	202438	Grey FGL e.c.	1.0	Bk-112	6	4	4 - 5	3
	2021143	Grey 4GL 220%	1.0	Bk-62	4 - 5	3	4	3 - 4
	2021672	Black CA 1600%	2.00	Bk-22	4	3-4	4-5	3

 ZDHC Level 3 + GOTS 7,0

 ZDHC Level 3

 GOTS 7.0 approved

FASTNESS

Light	ISO 105-B02 – Xenon
Washing	ISO 105-C06 – 40°C 30 min – Stain on CO
Rubbing	ISO 105-X12 – 10 cycles -Stain on CO