













DUVASTER











Low Energy

			% O.W.F.	C.INDEX	LIGHT FASTNESS	SUBLIMATION	WASH FASTNESS	ACID PERSPIRATION
	202405	Yellow E3G 220%	0.50	Y-54	6	3	3	5
	202406	Red E-FBL 200%	1.0	R-60	6	3	3	5
	2021172	Blue ERNT 200%	1.0	B-56	6 - 7	3	3	5

Medium Energy

	202288	Yellow GNL 200%	1.0	Y-211	6	4	4	5
	202399	Red F3BS 150%	1.0	R-343	6	3 - 4	3 - 4	5
	202966	Rubine SE-GFL 200%	1.0	R-73	6	3	3 - 4	5
	2021218	Rubine SE-CBT 200%	1.0	V-33	6	4	3	5
	202675N	Violet BL 150%	1.0	V-57	6 - 7	4 - 5	4 - 5	4 - 5
	202493	Blue 2RLS	1.0	B-183	5-6	4	3 - 4	5
	202870	Green C6B Special	1.0	G-9	6	4	4 - 5	5
	202388	Navy CDNE 300%	3.0	MIX	4 - 5	3 - 4	4 - 5	5
	2021111	Black CDNE 300%	4.0	MIX	4 - 5	3 - 4	4 - 5	5

High Energy









	2021753	Yellow 6GLS	1.0	Y-114	6 - 7	5	5	5
	202018	Yellow C5G Conc.	1.0	Y-119	5-6	4 - 5	5	5
	2021875	Yellow Brown ECO 150% Spec.	1.0	O-30	6 - 7	4 - 5	3 - 4	4 - 5
	2021683	Scarlet ECR	1.0	R-153	5	3 - 4	3 - 4	5
	202443N	Red BS 200%	1.0	R-152	4 - 5	4 - 5	3 - 4	4 - 5
	2021212	Red BWF-T	1.0	MIX	4 - 5	4 - 5	5	5
	2021863	Rubine 2G 150%	1.0	R-167	5-6	3 - 4	4	5
	2021744	Bordeaux SE-BL 160%	1.0	V-57	6	4	4	4 - 5
	2021209	Blue Brill. SE-GLT 200%	1.0	B-60	7-8	4 - 5	4 - 5	5
	202459	Navy S2GL Conc.	3.0	B-79	5-6	4 - 5	4	4 - 5

 ZDHC Level 3 + GOTS 7,0

 ZDHC Level 3

 GOTS 7.0 approved

DUVASTER

XF Range			% O.W.F.	C.INDEX	LIGHT FASTNESS	SUBLIMATION	WASH FASTNESS	ACID PERSPIRATION
	2021210	Yellow Brown XF-T	2.0	Br. 19	6	4 - 5	4 - 5	5
	2021211	Scarlet XFN-T	2.0	MIX	6	4 - 5	5	5
	202443N	Crimson SHW	2.0	MIX	5-6	4 - 5	4 - 5	5
	2021214	Rubine XF-T	2.0	MIX	5	4 - 5	3 - 4	5
	2021212	Red BWF-T	1.0	MIX	4 - 5	4 - 5	5	5
	2021931	Turquoise XF-T	2.0	MIX	6	4 - 5	5	5
	202166	Navy SHW	3.0	MIX	5-6	4 - 5	4 - 5	5
	202548	Black SHW	5.0	MIX	5-6	4 - 5	4 - 5	5

 ZDHC Level 3 + GOTS 7,0

 ZDHC Level 3

 GOTS 7.0 approved

FASTNESS

Light	ISO 105-B02 – Xenon
Sublimation	ISO 105-P01 – 180°C 30 seg (Stain on PES)
Washing	ISO 105-C06 – 60°C 30 min DUVASTER Stain on PA DUVASTER Stain on CA
Perspiration	ISO 105-E04 – 37°C 4h. – Change of shade
Nitrogen Oxides	ISO 105-G01 – 3 cycles – Change of shade